Multilayer Polyethylene PERT-AL-PERT pipe

P197 - Pipe marking "Icma"



Description

Multilayer Polyethylene PERT-AL-PERT pipe, white colour; Working temperature 70°C, Working pressure 10 Bar, Max temperature 95°C.

PERT Polyethylene: Polyethylene of raised temperature resistance. Butt-welded aluminium core.

Manufactured in compliance with EN ISO 15875 standard.



Applications

- Floor heating systems
- Sanitary Installations
- Radiator connection

Products

Code	Size	Colour
88P197GH10099	16x2	White
88P197GH50099	16x2	White
88P197BQ10099	20x2	White
88P197BQ50099	20x2	White
88P197GP05099	26x3	White
88P197GQ05099	32x3	White

Technical features

Characteristics	Unit of measure	Values			
Pipe dimension	mm.	16x2	20x2	26x3	32x3
Outer diameter	mm.	16	20	26	32
Wall thickness	mm.	2 3		3	
Internal diameter	mm.	12	16	20	26
Aluminium tickness	mm.	0,2 0,5		0,5	0,6
Pipe weight	g/m	105	148	240	323
Pipe weight with water	g/m	218	337	554	854
Internal volume	l/m	0,113	0,189	0,314	0,531
Heat conductivity	W/m • K	0,4			
Expansion coefficient	mm/m • K	0,025			
Surface roughness	μm	1,5			
Oxygen diffusion	mg/(m² • d)	0			
Operating temperature	°C	70			
Operating pressure	bar	10			
Max. operating temperature	°C	95			
Smallest bend radius	mm	≥ 5 • D			

Multilayer Polyethylene PERT-AL-PERT pipe


P197 - Pipe marking "Icma"



/ Volume of pipes in liters per meter

Size	Volume liters/meter
16x2	0,113
20x2	0.189
26x3	0,314
32x3	0,531

Layers



Quality control

PE-RT / Al / PE-RT multilayer pipes production is subjected to continuous quality controls that allow to ensure product manufacturing in compliance with current standards.

The main controls concern the following characteristics:

• **Dimensional** (external, internal diameter, thickness): during production and on the finished product according to the EN ISO 3126 standard.

// Warnings

Store the pipe in its original packaging avoiding exposure to solar radiation, which could compromise the quality of the pipe. Avoid contact / impact with blunt materials that could damage the pipe, both during transport and during construction. The minimum degree of curvature during installation must not be less than 5 times the external diameter of the pipe. Do not use chemical solvents or similar when installing the pipe.